



View Our Website - www.schraderco.com
Call Today - 425-377-1550

Fender Rubber Specification

3BA 720 A₁₄, B₁₃, C₁₂, EA₁₄, F₁₇, G₁₁, K₂₁

3BA 620 A₁₄, B₁₃, C₁₂, EA₁₄, F₁₇, G₁₁, K₂₁

<u>Callout No.</u>	<u>Property Tested</u>	<u>ASTM Test Method</u>	<u>Acceptance Requirements</u>
7	Durometer hardness	D2240	70 +/-5 Shore A
6			60 +/-5 Shore A
20	Tensile strength	D412, die C	2000 psi min.
	Ultimate elongation	D412, die C	300% min
A14	Heat resistance: Change in hardness Change in tens. str. Change in ult. elong.	D573, 70 hrs. @ 100C	±10 max. -25% max. -25% max.
B13	Compression set	D395, method B, 22 hrs. @70C	25% max.
C12	Resistance to ozone	D1171, method A	100%
EA14	Water resistance	D471, 70 hrs. @100C	±10% max. (vol.)
F17	Low-temperature resistance	D2137, method A, 9.3.2, 3 min. @-40	non-brittle
G12	Tear Resistance	D624, die B	Not Specified must be set by agreement (Morse recommends 250 ppi, Min).