

COMPARISON OF POLYMERIC COATINGS:

Manufacture's Name	Product Name	Date Entered	Source	Elongation	Reference	Tensile Strength	Reference
Poly Granite	PG-SL08	6/11/2009	Data Sheet	550%		2600psi	
	21 Poly	6/11/2009	Am Pole	585%+/-50	@ 77.25 F	3000+/-100	

Tear Resistance Reference	Hardness Reference	UV Change Reference	Flame Spread Reference Rating
520lb/in 480+/-50PLI	90-95A 90+/- Shore A		1.52cm/min ASTM D635

Abrasion Weight Loss	Reference	Permeability	Reference	VOC Content	Reference
210mg	1000rev H-18 Wheel	0.067 WVT		0%	