

## **SPECIFICATIONS FOR ACZA TREATED DOUGLAS FIR CAMEL LOGS**

### 1. SCOPE

1.1 This specification covers the type and size of log along with the ACZA treatment requirement for Douglas Fir logs.

### 2. REQUIREMENTS for LOG

2.1 Species. All logs shall be coastal Douglas Fir, round and sound.

2.2 Size. Camel Logs shall be lathe peeled to target diameter (15.5”)

2.3 Surface Condition. Logs shall be peeled as to have a smooth surface.

### 3. TREATMENT

#### 3.1 General References

A. American Wood Protection Association (AWPA) Book of Standards

1. Standard U1, Use Category System: Specification for Treated Wood
2. Standard P5, Waterborne Preservatives

#### 3.2 Manufacturers

A. Preservative Treatment: In accordance with the requirements of AWPA Standard U1 and in accordance with the following Commodity Specification:

1. Marine (Salt Water) Application

B. Preservative Retention: In accordance with the specified standard, determined in the specified zone for the following use category:

1. UC5B Salt or brackish water south of San Francisco – 2.5 lbs/ cubic foot

C. Treated Material: Provide treated logs that bear the quality mark of an ALSC recognized agency or written documentation which maintains supervision, testing, and inspection of the quality of the product.

### 4. POLYUREA COATING (Attached)